

Pecora-Deck Self Priming Additive (SPA)



SPECIFICATION DATA SHEET

MANUFACTURER

Pecora Corporation
165 Wambold Road
Harleysville, PA 19438
Phone: 215-723-6051
800-523-6688
Fax: 215-721-0286
Website: www.pecora.com

PRODUCT DESCRIPTION

Pecora-Deck™ Self Priming Additive is an additive used in the Pecora-Deck series of deck coating products. Pecora-Deck SPA is utilized in the 802 and 802FC elastomeric base coats to enhance adhesion to concrete and plywood deck surfaces. When using the Pecora-Deck SPA, the use of a primer is not necessary.

Typical Use:

Pecora-Deck Self Priming Additive is used as an adhesion additive to urethane base coats Pecora-Deck 802 and 802FC when being applied over unprimed concrete or plywood.

Use with:

Pecora-Deck 802 Base Coat
Pecora-Deck 802 FC Base Coat

Precautions:

Before use refer to SDS for important warnings and safety information. Avoid contact with skin, eyes or clothing. The use of gloves, aprons or other protective devices is recommended. In case of skin contact, wash thoroughly with soap and water. If contact with eyes is made, flush thoroughly with clear water and get medical attention.

Usage:

Add one unit of Pecora-Deck SPA to one 5 gallon unit of Pecora-Deck 800 or 800FC base coat. Using a typical paint mixing paddle comparable to a Jiffy mixer, mix the material from the bottom, being careful to avoid air entrainment for a minimum of 3 minutes.

Field testing for proper adhesion to construction surfaces is always recommended. Consult Pecora Technical Bulletin PEC 184 for proper field adhesion test procedures.

WARRANTY

Pecora Corporation warrants this product to be free of defects. Under this warranty, we will provide, at no charge, replacement materials for, or refund the purchase price of, any product proven to be defective when installed in accordance with our published recommendations and in applications considered by us as suitable for this product. This warranty is in lieu of any and all other warranties, expressed or implied, and in no case will Pecora be liable for incidental or consequential damages.

PACKAGING


- 7 oz. in ½ pint metal can
- A 2 year shelf life from date of manufacture when stored at 85°F or below can be expected.

Technical Services:

Pecora representatives are available to assist you in selecting an appropriate product and to provide on-site application instructions. For further information and assistance, please call our Technical Service department at 215-723-6051 or 800-523-6688.

FILING SYSTEMS

CSI MasterFormat Designations:
- 07 18 00: Traffic Coatings



Since Pecora Architectural Sealants are applied to varied substrates under diverse environmental conditions and construction situations it is recommended that substrate testing be conducted prior to application.